

S-500 QS (QUICK SETTING) SETTING & GROUTING EPOXY

PRODUCT DESCRIPTION:

S-500 QS is a Tile Council of America formula AARII-HT, epoxy mortar and grout that meets or exceeds requirements of ANSI A118.3 and is USDA approved. S-500 QS is a three-part 100% solids epoxy formulation that allows installation to be open to traffic in 4 to 6 hours.

S-500 QS has the same physical properties and chemical resistance as S-500.

S-500 QS is sag resistant and should be specified for setting or grouting ceramic tile on any wall or floor installation. This product has exceptional bond strength and will remain rigid and cohesive at temperatures up to 350°F. S-500 QS will resist attacks by many acids, alkalies and other chemical compounds that will normally break down cement mortars and grouts.

Floor brick, quarry tile, pavers and ceramic mosaics may be set and grouted with S-500 QS.

NOTE: When more stringent chemical resistance is encountered, S-4000 Furan or S-5000 high chemical resistant epoxy should be used.

USES:

S-500 QS is recommended when a quick-set formula is required in food processing plants, dairies, breweries, chemical laboratories, distilleries and refineries.

LIMITATIONS:

Surface temperature of substrate should be above 50°F during tile installation. Continuous exposure of cured S-500 QS above 350°F is not recommended.

TECHNICAL DATA Physical Properties:

Hardness (Shore D) 7 days	70-80
Hardness (Shore D) 28 days	80-90
Linear shrinkage, %	0.01
Compressive strength, psi (ASTM C-109)	greater than 6000
Shear bond strength, psi (ANSI-A118.3 E-5.5.2)	1200
Tensile strength	1200 psi
Pot life at 72°F, mins.	20-30
Cure time at 72°F, hrs.	12-16
Temperature limitation, °F	350
Working time, min.	less than 60
Sag using 6" x 6" x 1/2" Quarry tile	0.00

INSTALLATION:

Substrate: S-500 QS is recommended for use on *cured* concrete, plaster, drywall, masonry surfaces, cementitious backerboard and plywood. Substrate shall be prepared in accordance with ANSI A108.4.

Surface to receive S-500 QS must be structurally sound, dry, free of sealers, coatings, oil, dirt and dust. New masonry surfaces should be sufficiently cured, dimensionally stable and free from cracks. It is advisable to brush all surfaces with a stiff brush to remove any loose material that may be encountered. Consult the Tile Council "Handbook for Ceramic Tile Installations" for specific setting descriptions.

Mixing: S-500 QS is furnished in three parts and thorough mixing of the parts with one another is absolutely essential for satisfactory performance, A 1-1/2 gallon unit requires one bag of part C powder. A three-gallon unit requires two bags of part C

powder. Before weighing from containers, mix each part thoroughly to ensure uniformity within the part. Empty contents of parts A and B into mixing bucket and mix to uniform color and consistency. Gradually add part C powder and mix thoroughly using either hand tools or a slow spin power mixer. (e.g. bucket mixer) Mix until all part C is uniformly wetted, smooth, and free of lumps. *Care must be taken to avoid whipping air into this mix.* It is recommended that complete units be mixed at a time; however, if necessary to split a unit, weigh out three parts A, one part B, and 8 parts C by weight, not by volume. Clean tools with warm soapy water immediately after use.

Working Characteristics: S-500 QS is ideally installed at temperatures from 70°-80F. At higher temperatures, the pot life, open time, and clean-up time are reduced; however, it is more fluid and easier to work. At lower temperatures these factors are reversed. Working surface temperature can vary from room temperature and should be taken into consideration. Do not begin application of S-500 QS until the temperature of the room and substrate is above 50°F and rising. Maintain a temperature of 60°F or higher during the curing period.

Material must be stored at 60-80°F for 24 hours before using.

Temperature	Pot Life	Open Time	Clean-Up Time	Set Time
60°F (16° C)	45-60 min.	2 hrs.	45-60 min.	3-4 hrs.
75°F (24° C)	20-30 min.	1 hrs.	35-45 min.	2-3 hrs.
90°F (32° C)	10-15 min.	42 min.	10-15 min.	1-2 hrs.

APPLICATION:

As a Setting Mortar: Spread mixed S-500 QS with a notched trowel, then set tile. Use a 1/8" notched trowel for ceramic mosaics to achieve a 1/16" bed. Use a 1/4" notched trowel for smooth or shallow ribbed pavers providing a finished bed of 1/8". Use a 1/4" x 3/8" square notched trowel for heavy ribbed backed tile such as Quarry tile.

Full coverage of the setting material on the back of the tile is desirable to prevent broken and cracked tile. The National Tile Contractors Association recommendation to accomplish full coverage is as follows: Apply mortar to substrate using the flat side of the trowel to fill any voids and "key" the material to the substrate. Using the proper sized notched trowel, comb the mortar evenly in one direction only. Do not "swirl". Set the tile in the mortar with the edge of the tile parallel to the comb lines. To remove air voids, push the tile back and forth in the mortar perpendicular to the comb lines.

Once S-500 QS begins to set, it should be discarded, as proper bonding will not be accomplished. Allow minimum of 5 hours to elapse before grouting tile.

As a Grout: With a firm, straight edge rubber trowel (Grout Master) force as much S-500 QS into joints as possible, using sufficient pressure and flow to avoid air pockets or voids. Before the S-500 QS loses its plasticity, remove excess with rubber trowel in a squeegee fashion working diagonally to joints to facilitate removal without pulling material from joints.

CLEAN-UP:

For initial clean-up, use a white plastic scrub pad and a lot of clean water. Avoid water migration into ungrouted joints. Warm water with a few drops of a mild soap added will speed clean-up. Change cleaning water often to avoid leaving a sticky film on the tile. Do not leave standing water on uncured epoxy joints after initial cleaning. Perform final clean up after 5 hours but before 10 hours. Use a white scrub pad and soap and water. Clean completely, as S-500 QS is difficult to remove after it cures for over 10 hours. Wide tile joints may have a slight concave appearance after grout cure. Cover with kraft paper and plywood after final clean up to protect from other construction debris during cure period.

Grout Coverage: *S-500 QS

Tile Size	*S-500 QS Joint Width		
	1/8"	1/4"	1/2"
4" x 8" x 1/2"	79	40	20
4" x 8" x 3/4"	53	27	13
4" x 8" x 1"	40	20	10
4" x 8" x 1 3/16"	33	17	8
4" x 8" x 1 3/8"	29	15	7
4" x 8" x 1 1/2"	26	13	7
4" x 8" x 2 1/4"	18	9	5
4" x 12" x 1/2"	97	49	24
6" x 6" x 1/2"	84	42	21
6" x 6" x 3/4"	56	28	14
6" x 9" x 3/4"	69	35	17
5" x 10" x 3/4"	66	33	17
5" x 10" x 1 1/2"	33	17	8
8" x 8" x 3/8"	149	75	37
8" x 8" x 1/2"	112	56	28
8" x 8" x 1"	56	28	14

*Epoxy coverage is in sq. ft. per gallon.

COVERAGE:

Setting: Sq. ft./gallon unit using 1/4" x 1/4" sq. notched trowel

18-20

CAUTION:

Protect from dirt and all traffic for 4-6 hours, heavy traffic and dirt for 48 hours. Do not grout in direct sunlight. Cure S-500 QS a minimum of seven days at 70°F before chemical exposure.

PROTECTING NEW TILEWORK:

To avoid damage to finished tilework, schedule floor installations to begin only after all structural work, building enclosure, and overhead finishing work, such as ceilings, painting, mechanical and electrical work are completed. Keep all traffic off of finished tile floors until it has fully cured, or provide up to 3/4" thick plywood protection over Kraft paper to protect floors before installation materials have fully cured.

PACKAGING:

S-500 QS is available in 1.5 and 3 gallon sizes, which include resin and hardener; filler powder is sold separately. A 1.5-gallon unit requires one 12.5-pound bag of part C powder, a 3-gallon unit requires two 12.5-pound bags of part C powder.

COLORS:

Snow White 913, Red S2063, Plum S2163, Green S3033, Cayman Green S3143, Brown S4013, Black S5013, Tan S6023, Buff S6073, Smoke S7133, Grey S7043, Blue S8043, White S9073. Custom colors are available with minimum quantity.

SPECIFICATIONS:

Material: Setting mortar and tile grout shall be S-500 QS, a three-component mix consisting of specially graded silica aggregate (#7 on M.O.H. Scale of Hardness), color-fast pigments, a special blend of activating hardeners and liquid epoxy resin, and be free of water and organic solvents; as manufactured by Summitville Tiles, Inc., Summitville, Ohio. The material in the mixed state shall not allow tile to sag on vertical surfaces and in the reacted state shall remain rigid and cohesive in temperatures up to 350°F. Acid and alkali resistant epoxy mortar and grout shall meet or exceed ANSI A118.3.

Color: Color shall be #

CHEMICAL RESISTANCE GUIDE FOR S-500 & S-500 QS

CHEMICAL	S-500 (AARII-HT)	S-500QS (Quick Setting Epoxy)	CHEMICAL	S-500 (AARII-HT)	S-500QS (Quick Setting Epoxy)	CHEMICAL	S-500 (AARII-HT)	S-500QS (Quick Setting Epoxy)	CHEMICAL	S-500 (AARII-HT)	S-500QS (Quick Setting Epoxy)	CHEMICAL	S-500 (AARII-HT)	S-500QS (Quick Setting Epoxy)
Acetic Acid, Glacial	N	N	Barium Hydroxide	R	R	Calcium Chloride	R	R	Formic Acid Glacial	N	N	Potassium Hydroxide 5%	R	R
Acetic Acid 10%	C	C	Beer	R	R	Calcium Hydroxide	R	R	Formic Acid 10%	C	C	Potassium Persulfate 50%	R	R
Acetic Acid 3%	R	R	Benzyl Acetate	C	C	Carbon Disulfide	C	C	Hydroiodic Acid 20%	R	R	Pyridine 20%	C	C
Acetic Anhydride	N	N	Benzyl Alcohol	N	N	Carbon Tetrachloride	R	R	Hydrobromic Acid 10%	R	R	Saturated Sugar Solution	R	R
Acetone	C	C	Benzaldehyde	N	N	Chloroacetic 50%	N	N	Hydrochloric Acid 37%	R	R	Sodium Carbonate	R	R
Ammonia (household)	R	R	Benzene	N	N	Chloroacetic 10%	N	N	Hydrochloric Acid 10%	R	R	Sodium Hydroxide 35%	R	R
Ammonium Bromide 30%	R	R	Bromine Water	R	R	Chlorobenzene	N	N	Lactic Acid 3%	C	C	Soy Sauce	R	R
Alcohol	R	R	Butanol	R	R	Chlorine Water (bleach)	R	R	Lactic Acid 10%	N	N	Sulfuric Acid 10%	R	R
Aniline	N	N	Butyl Acetate	C	C	Chromic Acid 10%	R	R	Lactic Acid 30%	N	N	Sulfuric Acid 45%	R	R
						Citric Acid 20%	R	R	Nitric Acid 50%	N	N	Sulfuric Acid 95%	N	N
						Cooking Grease	R	R	Nitric Acid 10%	R	N	Tetrahydrofuran	N	N
						Cresol	N	C	Nitrobenzene	N	N	Trisodium Phosphate	R	R
						Ethyl Bromide	N	C	Nitrotoluene	R	R	Vegetable Oil	R	R
						Ethylene Glycol Monobutylate	R	R	Phenol	N	N	Wine	R	R
						Ferric Chloride	R	R	Phosphoric Acid 10%	R	R			

R = Recommended
N = Not Recommended

C = Conditional
Contact Summitville Tiles, Inc. before installation



Summitville Tiles Inc. • Summitville, Ohio 43962
(330) 223-1511 • FAX (330) 223-1414
www.summitville.com

